



Caractéristiques du mélange : 0/20

MF : 5.65 – D10 : 0.25 – D30 : 1.60 – D60 : 5.60 – D70 : 10.0 – Cc : 1.83 – Cu : 22.40

LaboWin®

| références essais                      | Masse(s)<br>à mélanger | Proportion(s)<br>du mélange |
|--|------------------------|-----------------------------|
| 0/4 R haute marne fraction:0.050/8.00  | 550.0                  | 55.0                        |
| 4/20 R haute marne fraction:0.050/28.0 | 450.0                  | 45.0                        |
|  |                        |                             |
|  |                        |                             |
|  |                        |                             |
| <b>Total :</b>                         | 1000.0                 | 100 %                       |

Le responsable

*[Signature]*

Le 16 janvier 2019

LA = 24.68

SE = 84

